



Meteorwave 8350 – Dielectric Properties Table

LAMINATE:

Thickness	&	Tol.	Construction						RC%	2GHz Dk	2 GHz Df	10 GHz Dk	10 GHz Df	40 GHz Dk	40 GHz Df
0.0020	±	0.0005	1	1078					58%	3.52	0.0014	3.49	0.0018	3.48	0.0021
0.0035	±	0.0005	1	1078	+	1	1035		58%	3.52	0.0014	3.49	0.0018	3.48	0.0021
0.0045	±	0.0005	2	1078					58%	3.52	0.0014	3.49	0.0018	3.48	0.0021
0.0050	±	0.0007	1	2116					58%	3.52	0.0014	3.49	0.0018	3.48	0.0021
0.0050	±	0.0007	1	1035	+	1	2013		58%	3.52	0.0014	3.49	0.0018	3.48	0.0021
0.0060	±	0.0007	1	2013	+	1	1078		58%	3.52	0.0014	3.49	0.0018	3.48	0.0021
0.0080	±	0.001	2	2013					58%	3.52	0.0014	3.49	0.0018	3.48	0.0021
0.0090	±	0.001	1	2116	+	1	2013		58%	3.52	0.0014	3.49	0.0018	3.48	0.0021
0.0100	±	0.001	2	2116					58%	3.52	0.0014	3.49	0.0018	3.48	0.0021
0.0130	±	0.0015	2	2013	+	1	2116		58%	3.52	0.0014	3.49	0.0018	3.48	0.0021
0.0150	±	0.0015	4	2013					58%	3.52	0.0014	3.49	0.0018	3.48	0.0021
0.0180	±	0.0015	2	2013	+	2	2116		58%	3.52	0.0014	3.49	0.0018	3.48	0.0021
0.0200	±	0.0025	4	2116					58%	3.52	0.0014	3.49	0.0018	3.48	0.0021
0.0210	±	0.0025	5	2013	+	1	1078		58%	3.52	0.0014	3.49	0.0018	3.48	0.0021
0.0250	±	0.0025	5	2116					58%	3.52	0.0014	3.49	0.0018	3.48	0.0021
0.0300	±	0.0025	6	2116					58%	3.52	0.0014	3.49	0.0018	3.48	0.0021
0.0600	±	0.005	12	2116					58%	3.52	0.0014	3.49	0.0018	3.48	0.0021
0.0620	±	0.005	12	2116	+	1	1035		58%	3.52	0.0014	3.49	0.0018	3.48	0.0021



Meteorwave 8350 – Dielectric Properties Table

PREPREG:

Glass	RC%	2 GHz Dk	2GHz Df	10GHz Dk	10GHz Df	Thickness (inches)	Thickness (µm)
1078	58	3.52	0.0014	3.49	0.0018	0.0023	58.7
2013	58	3.52	0.0014	3.49	0.0018	0.0040	100.7
2116	58	3.52	0.0014	3.49	0.0018	0.0051	129.3

The following laminate and prepreg items are a representative of available materials. These items and their associated values may not be regularly available and additional lead times or minimum order quantities could apply. Please contact our office or your local technical representative for assistance with choosing the best material for your design and application.

For More Information:

North America +1.480.967.5600 • Europe +33.5.62.98.52.90 • Asia Pacific +65.686.17117

agc-ml.multimaterial@agc.com • www.agc-multimaterial.com

August 12, 2025